WRA

Dimensions in mm.

Reduction of load rating for linear ball bearing because of less hardness.

Other types available on request.

Material: X90CrMoV18 / 1.4112.
Surface hardness: 54 HRC min. Hardening depth according to DIN ISO 18203.
Standard Tolerance: ISO h6




Every care has been taken to ensure the accuracy of the information in this document, but we take no liability for any errors or omissions. We reserve the right to make changes without prior notice.

General Data

Designation	Weight (kg/m)
WRA8	0.39
WRA10	0.62
WRA12	0.89
WRA14	1.21
WRA16	1.58
WRA20	2.47
WRA25	3.85
WRA30	5.55
WRA40	9.86
WRA50	15.41

Every care has been taken to ensure the accuracy of the information in this document, but we take no liability for any errors or omissions. We reserve the right to make changes without prior notice.

Dimensions



Designation	Lw (mm)	Diameter	Hardening Depth	Roundness t1	Parallelism t2	Straightness t3
WRA8	6000	8	.4	4	6	.3
WRA10	6000	10	.4	4	6	.3
WRA12	6000	12	.6	5	8	.3
WRA14	6000	14	.6	5	8	.3
WRA16	6000	16	.6	5	8	.2
WRA20	6000	20	.9	6	9	.2
WRA25	6000	25	.9	6	9	.2
WRA30	6000	30	.9	6	9	.2
WRA40	6000	40	1.5	7	11	.2
WRA50	6000	50	1.5	7	11	.2

Every care has been taken to ensure the accuracy of the information in this document, but we take no liability for any errors or omissions. We reserve the right to make changes without prior notice.